

●/PR 7S

SPECIFICATION

PROCESS FOR PRODUCING LEAD-ACID BATTERY, AND  
JIG FOR PRODUCING LEAD-ACID BATTERY

TECHNICAL FIELD:

A present invention relates to a process for producing a lead-acid battery and more particularly, a process for producing a lead-acid battery related to welding of terminal portions of the battery, and a jig for producing the same.

BACKGROUND ART:

It is a conventional practice either to produce a lead-acid battery of a so-called bushing terminal type in which a lead bushing also serves as a terminal, by inserting an upper portion of a pole protruding upwards from a cell chamber within a battery container of an assembled lead-acid battery through an insertion hole in a lead bushing cast in a lid made of a synthetic resin by a cast molding process, and welding the pole inserted and the lead bushing around an outer periphery of the pole to each other, or to produce a lead-acid battery of a type having a terminal member led out sideways by mounting a separately fabricated terminal on an outer peripheral surface of a lead bushing, and welding the bushing and the terminal to each other using a burner.

In this case, at the time of welding using the burner, as mentioned above, in order to previously prevent that the lid would be deformed due to a welding heat, whereby an air-tightness failure would occur between the lid and the lead bushing

09/857187:023001

More particularly, in the case of producing the lead-acid battery of a bushing terminal type as described above, it has been conventional to weld terminal portions to be welded of the lead-acid battery, i.e., mutually abutted or adjacent peripheral portions of the lead bushing integrally cast in a lid made of a synthetic resin by an insertion molding and a pole of a battery body inserted through a cylindrical hole in the lead bushing to each other by a burner flame.

In the case of welding of the pole and the lead bushing using the burner, however, if the height from the surface of the lid to an upper end surface of the lead bushing is not more than 8 ~ 10 mm, in other words, is less than 8 ~ 10 mm, it is not avoidable that the lid is deformed due to the heat generated during the burner-welding, even if the above-mentioned cooling means is used, an air-tightness failure is occurred between the lid and the lead bushing formed in the lid. Therefore, it is required that the upper end of the lead bushing protrudes more than 8 ~ 10 mm from the surface of the lid, and hence, such a corresponding height-wise space enough to accommodate the lead bushing terminal is required above the upper surface of the lid. On the other hand, it is desirable to produce a lead-acid battery

Therefore, it is desired to remove such inconveniences and develop a process capable of producing a lead-acid battery, wherein welding of the required portions can be achieved smoothly without any manufacture loss.

Accordingly, it is desired to remove such inconveniences and develop a process for producing a lead-acid battery by such a process for welding of the terminal portions that is capable of welding the terminal portions to each other stably and

Accordingly, it is desired to remove such inconveniences and develop a process for producing a lead-acid battery by such a process for welding of the terminal portions that is capable of welding the terminal portions to each other stably and

**SECRET**

It is an object of the present invention to provide a process for producing a lead-acid battery which has removed the problems associated with the prior arts, and the present invention is characterized in that a lead bushing integrally cast in a lid of an assembled lead-acid battery and a pole inserted through the lead bushing are welded together by a laser welding.

Further, in the process for producing the lead-acid battery according to the present invention, it is characterized in that at the time of the laser welding a laser beam of a low output is applied and thereafter a laser beam of a high output is applied.

Further, in the process for producing the lead-acid battery according to the present invention, it is characterized in that the lap density of beads in the laser welding of the pulsed type is in a range of 6 ~ 12 points per mm.

Further, it is an object of the present invention to provide

00357187 062001

a process for the laser welding of the terminal portions of the lead acid battery for preventing a laser beam from intercepting by fumes generated at the time of application thereof in the laser welding in the process for producing the above-mentioned lead-acid battery, to make it possible to carry out the welding at a high efficiency and stably and sufficiently, and it is characterized in that when the laser-welding is carried out by applying the laser to terminal portions to be welded of the lead-acid battery, there is used such a process for laser-welding of the terminal portions that the terminal portions are surrounded by a lower cylindrical end portion of a cylindrical shield, and, in this state, fumes generated at the time of the laser-welding are sucked to be exhausted to the outside of the cylindrical shield through an exhaust port in the cylindrical shield.

Further, it is an object of the present invention to provide a process for the laser welding of the terminal portions which is capable of carrying out the welding by application of the laser beam accurately and at a good efficiency when the above-mentioned process for laser welding is used in the above-mentioned process for producing the lead-acid battery, and it is characterized in that a discharge opening is provided in the cylindrical shield, and oxygen or air is supplied through the discharge opening to the portions to be welded.

Further, it is an object of the present invention to provide a process for laser welding for carrying out the laser welding more accurately and at a better efficiency when the

above-mentioned process for laser welding is used in the above-mentioned process for producing the lead-acid battery, and it is characterized in that a shroud ring having the plural of communication openings made circumferentially in its peripheral wall is installed in the cylindrical shield with an annular space left between the shroud ring and the inner peripheral wall surface of the cylindrical shield so that fumes generated in the shroud ring may be sucked to be exhausted out of the cylindrical shield through the communication holes of the shroud ring, the annular space surrounding thereof and the exhaust port, together with a shielding fluid flowed through the discharge opening into the cylindrical shield.

Further, the present invention, which is capable of carrying out the laser welding at a better efficiency while removing the fumes at a good efficiency by the laser welding when the above-mentioned laser welding is used in the above-mentioned process for producing the lead-acid battery, and it is characterized in that the plural communication bores made at regular intervals in the shroud ring are formed into those which are open in a circumferentially tangent direction of the ring, whereby an eddy flow is occurred to the fumes generated inside the shroud ring and is sucked to be exhausted.

Further, it is an object of the present invention to provide a laser welding jig which is suitable for carrying out the above-mentioned process for producing the lead-acid battery, and it is characterized in that an opening of the upper surface of a cylindrical body made of a metal having a good heat

009357187 0622004

conductivity is closed by a light-transmission plate and a lower cylindrical portion thereof is adapted to be fitted on the outer peripheral surface of the terminal portions of a lead-acid battery, so that a cylindrical shield is formed, and the cylindrical shield is provided with the plural discharge openings for a shield fluid disposed circumferentially at the lower portion thereof, and a shroud ring provided with the plural communication openings disposed at regular intervals circumferentially at a position which is above the discharge openings is so installed in the cylindrical shield as to leave an annular space between the shroud ring and the inner surface of a peripheral wall of the cylindrical shield, and the cylindrical shield is provided with an exhaust port which communicates with the annular space.

The disclosure of other characteristics of a process for producing a lead-acid battery and a welding jig used for the same according to the invention will be made clear in detail hereinafter.

#### BRIEF DESCRIPTION OF THE DRAWINGS:

Fig.1 is a partially cutaway side view of one example of an embodiment of a process for producing a lead-acid battery according to the present invention.

Fig.2 is a top view of a terminal portion of the lead-acid battery shown in Fig.1.

Fig.3 is a diagram for explaining a lap density of welding beads.

Fig.5 is a top view of a terminal portion of the lead-acid battery shown in Fig.4.

Fig.7 is a sectional view taken along a line VI-VI in Fig.6.

Fig.9 is a partially cutaway perspective view for illustrating one example of a process for laser welding used in the present invention.

Fig.11 is a graph for explaining a most preferable embodiment of a laser-welding process for use in the process for producing the lead-acid battery according to the present invention.

Fig.13 is a centrally vertical sectional view of another embodiment of an apparatus used in a process for producing a



lead-acid battery according to the present invention.

#### BEST MODE FOR CARRYING OUT THE INVENTION:

The present invention will now be described in detail for more clarification, with reference to the accompanying drawings.

Figs.1 and 2 show one embodiment of the present invention suited for to a process for producing a lead-acid battery of a type having a lead bushing terminal. Fig.1 is a partially cutaway side view of an assembled lead-acid battery A in such a state that a laser nozzle connected to a laser-generating device (not shown) is disposed above the upper surface of terminal portions of a pole to be welded of the assembled lead-acid battery A, and Fig.2 is a top view of a lid thereof.

More specifically, the assembled lead-acid battery A comprises a mono-block type lead-acid battery, for example, comprising six cells. In the drawings, reference character a designates a molded battery container made of a synthetic resin such as polypropylene, and reference character b designates a molded lid for the battery container which is abutted against and air-tightly bonded to the upper surface of the container a, which has an upper flat surface and which is provided with a lead bushing 1 integrally cast therein by a casting process using a synthetic resin such as polypropylene as a raw material. The lead bushing 1 is preferable to be made using, preferably, lead alloys such as Pb-Ca-Sn, etc. as a material. According to the present invention, the lead bushing 1 is so cast that a projected height h from the upper surface of the lid b to the

F00250-2B72580

Cells contained in respective cell chambers c in the container a are connected in series, as usual, and the lead-acid battery is assembled in such a manner that an upper portion 2a of a positive pole 2 protruding upwards from a strap e connecting, for example, ears of the positive plates d, d, ... among positive and negative plates constituting the cell in the cell chamber c at one end of the container a is inserted through an insertion hole 3 of the lead bushing 1 located at a corner portion of one side of the container lid b, as shown in the drawings, and an upper portion of a negative pole protruding upwards from a strap connecting negative plates of the cell in the cell chamber at the other end of the container a is inserted through an insertion hole in a lead bushing likewise cast therein, though not shown. According to the present invention, the upper portion 2a of the positive pole 2 of the lead-acid battery thus assembled and the projection portion 1a of the lead bushing 1 around the outer peripheral surface thereof are welded together by a laser welding, and the upper portion of the negative pole and the projection of the lead bushing around an outer periphery thereof are welded together similarly by a laser welding. For convenience, only the laser welding of the pole 2 which is the positive pole and the lead bushing 1 on one side as shown in Fig.1 will be described below in detail. The description the laser welding on the negative pole side is omitted, because it is carried out in the

According to the present invention, a laser-welding nozzle 4 is placed at a desired height distance spaced apart from the upper end of the lead bushing 1 above the positive pole 2 and the lead bushing 1 around the outer periphery thereof, and a plate-shaped transparent shield glass 5 is placed below the welding nozzle 4. The shield glass 5 is disposed just below the nozzle 4 through a support leg 6 depending vertically therefrom, or is placed on the upper surface of a cylindrical mold 7 which is placed on the upper surface of the lid b, and also is fitly mounted on the outer peripheral surface of the projection 1a of the lead bushing 1 to support the lead bushing 1, as shown by phantom lines. The mold 7 shown in the drawings, in other words, a jig is a cylindrical mold made of copper having a good thermal conductivity which also serves acts to cool the lead bushing 1 heated during the welding, and the inner peripheral surface of the upper portion thereof is formed into a trumpet-shaped slant surface 7a spread upwards, so that the shield glass 5 is placed stably on the inner peripheral slant surface 7a. It is not necessary for mold 7 made of copper to provide an equipment of a jacket type through which cooling water is passed as conventional, and to carry out a cooling operation while passing water therethrough. The shield glass 5 is for protecting the laser nozzle 4 from deposition of sputtered lead produced when a laser beam 4b from the laser nozzle 5 is applied to the upper surfaces of the pole 2 and the lead bushing 1 as shown in Fig.1 for welding them to each other. The height

The nozzle 4 is connected to a predetermined laser-generating source not shown through an optical fiber 4b. A type of a laser is for example, a YAG laser by which the laser welding according to the present invention is carried out. A method of the laser welding may be either a continuous welding one or a pulsed welding one, but, in a case where the depth of weld (penetration) of lead or a lead alloy is required to be made deep, the pulsed welding method is preferable. The laser welding according to the present invention is carried out by applying a laser beam of an high output, for example, 6 ~ 8 Joules enough to weld the lead or lead alloy, to and along the mutually abutted or adjacent circular portions 8 of the outer peripheral surface of the pole 2 and the outer peripheral surface of the lead bushing 1 or their vicinities, and moving it at least one round while welding the portions 8 together, so that welding between the pole 2 and lead bushing 1 is welded together to form a laser-welded terminal portion. It is sufficient if the depth of weld or penetration of the laser-welded portion is at least about 2.5 mm. The present inventors have found that, according to this laser-welding, even if the height of the lead bushing 1 from the upper surface of the lid b is only 4 mm, a stable and good welding the pole 2 and the bushing 1 together can be achieved without occurrence in the thermal deformation of the lid b. Accordingly, in respect of the lead-acid battery thus produced according to the present invention, the lead bushing

In addition, the pole 2 and the bushing 1 are made of lead or a lead alloy, and it is general and preferable that both members are made using the same material.

When the laser welding according to the present invention is carried out, the following phenomenon has been found.

Namely, when a laser beam of a high output is applied from the beginning to the surface of the lead busing 1 and that of the pole 2, it has been observed that the lead or lead alloy on the surfaces thereof is sputtered vigorously and explosively to become so-called sputtered lead and adhere to the surface of the shield glass 5 positioned thereabove, and thereby the laser beam is intercepted. Therefore, the laser welding is carried out sufficiently at the start of the laser welding, but the laser welding power is reduced with the lapse of time and

thus, there is a fear that the mutually abutted annular portions 8 cannot be welded to each other sufficiently by the laser welding. As a result of various experiments, it has been proved that if in the first place, a laser beam 5b is applied at such a low output that produces no sputtering and is moved one round along the entire circumferential surfaces of the pole and the lead bushing, and thereafter it is applied at a high output, a satisfactory laser-welding is achieved at a high efficiency and with a high energy over the entire circumferential surfaces thereof.

A comparison test example will be described in detail below.

At the time of welding the whole circumferences of the mutually abutted annular portions 8 of the pole 2 and the lead bushing 1 to be welded by the pulsed laser-welding, respective welded portions obtained by such a laser-welding case (an example of the present invention) that a laser beam of a low output as low as  $0.8 \sim 1.5$  Joules /pulse was firstly applied to the fire entirely circumferential surfaces of mutually abutted portions 8 and the vicinities thereof to break the lead oxide film, and a laser beam of a high output as high as  $6 \sim 8$  Joules/pulse was then applied to the entire circumferences thereof, thereby achieving the laser welding, and by such a laser-welding case (a comparative example) that a laser beam of a high output as high as  $6 \sim 8$  Joules/pulse was carried out from the beginning, were cut, respectively, by a line connecting between a starting point of the welding 8a indicated by a mark X on the mutually

100290-2072550

abutted annular portions 8 in Fig.2 and a mid point 8b of the welding which is on the opposite side of the welding-starting point 8a and indicated by a mark  $\Delta$ , and a depth of weld (penetration) of each of the respective welded portions of the cut surfaces thereof was measured, and there were obtained the results shown in Table 1 below.

Table 1

	Depth (mm) of weld (penetration)	
	Starting point of the welding	Mid point of the welding
Example	2.4 ~ 2.6	2.4 ~ 2.6
Comparative Example	2.4 ~ 2.6	1.5 ~ 2.0

As is clear from Table 1 above, when the laser beam of the low output was first applied and the laser beam of the high output is then applied, according to the present invention, there was obtained a good weld in which the depths of welds at both of the starting point of the welding and the mid point of the welding were the same about 2.5 mm which is a satisfactory weld. In contrast therewith when the welding is carried out using the laser beam of the high output from the beginning, there is obtained a good weld in which the depth of weld at the start point of the welding is about 2.5 mm which is a satisfactory weld, but the depth of weld at the mid-point of the welding in the course of the welding was as shallow as 1.5 ~ 2.0 mm which is found to be insufficient in the depth of weld. This difference between the superiority and the inferiority is particularly remarkable in a case of using any of Pb-Ca based alloys that an oxide film is produced on the surface thereof.

T00290 2375360

Further, it has been proved that when the pulsed laser welding was carried out by applying a laser beam of a high output to and along the mutually abutted portions 8, the number of the beads of the welding overlapped per 1 mm, i.e., a lap density of the beads, as shown in Fig.3, has various influences on the weld state, as described hereinafter.

Namely, 100 assembled lead-acid batteries as shown in Fig.1 were used as samples, and the welding was carried out in such a manner that a laser beam of a low output as low as 0.8 Joules/pulse was applied to the surfaces of the lead bushing 1 and the pole 2 of each of the 100 assembled lead-acid batteries, and thereafter a pulsed laser beam of a high output as high as 6 ~ 8 Joules/pulse was applied to the mutually abutted portions 8 by changing the lap density of the beads (having a diameter of 2 mm) variously. A depth of weld (penetration), a rate of generation of pinholes and a rate of generation of lack of air-tightness caused by the deformation of the lid were examined for each of the samples. Results are as shown in Table 2 below.

Table 2

Lap number of beads piled per mm (points)	Depth of weld (penetration) (mm)	Rate of generation of pinholes (%)	Rate of generation of lack of air-tightness (%)
0	0.8	48	0
3	1.4	20	0
6	2.5	0	0
9	3.0	0	0
12	3.3	0	0
15	3.9	0	27



On the other hand, in the case where the lap number of beads per mm was 6 points ~ 12 points, the depth of penetration was so deep as 2.5 ~ 3.3 mm, and also no pinhole passing through the penetration portion was generated to obtain stable and good laser-welds. In the case where the lap number of beads per mm was 15 points, it has been found that the depth of penetration became 3.9 mm, which was too deep, and the lid b was thermally deformed, and the air-tightness with the lead bushing cast in the lid b was broken to generate the lack of air-tightness.

Consequently, it has been found that in the case where the lap number of beads /mm within the length of 1 mm is in a range of 6 points ~ 12 points, stable and good laser welding can be carried out.

Figs. 4 and 5 show an embodiment of the present invention applied to a lead-acid battery of a type provided with a tab terminal member is prepared separately and welded to the lead

57-17

272156  
 272157  
 272158  
 272159  
 272160  
 272161  
 272162  
 272163  
 272164  
 272165  
 272166  
 272167  
 272168  
 272169  
 272170  
 272171  
 272172  
 272173  
 272174  
 272175  
 272176  
 272177  
 272178  
 272179  
 272180  
 272181  
 272182  
 272183  
 272184  
 272185  
 272186  
 272187  
 272188  
 272189  
 272190  
 272191  
 272192  
 272193  
 272194  
 272195  
 272196  
 272197  
 272198  
 272199  
 272200  
 272201  
 272202  
 272203  
 272204  
 272205  
 272206  
 272207  
 272208  
 272209  
 272210  
 272211  
 272212  
 272213  
 272214  
 272215  
 272216  
 272217  
 272218  
 272219  
 272220  
 272221  
 272222  
 272223  
 272224  
 272225  
 272226  
 272227  
 272228  
 272229  
 272230  
 272231  
 272232  
 272233  
 272234  
 272235  
 272236  
 272237  
 272238  
 272239  
 272240  
 272241  
 272242  
 272243  
 272244  
 272245  
 272246  
 272247  
 272248  
 272249  
 272250  
 272251  
 272252  
 272253  
 272254  
 272255  
 272256  
 272257  
 272258  
 272259  
 272260  
 272261  
 272262  
 272263  
 272264  
 272265  
 272266  
 272267  
 272268  
 272269  
 272270  
 272271  
 272272  
 272273  
 272274  
 272275  
 272276  
 272277  
 272278  
 272279  
 272280  
 272281  
 272282  
 272283  
 272284  
 272285  
 272286  
 272287  
 272288  
 272289  
 272290  
 272291  
 272292  
 272293  
 272294  
 272295  
 272296  
 272297  
 272298  
 272299  
 272300  
 272301  
 272302  
 272303  
 272304  
 272305  
 272306  
 272307  
 272308  
 272309  
 272310  
 272311  
 272312  
 272313  
 272314  
 272315  
 272316  
 272317  
 272318  
 272319  
 272320  
 272321  
 272322  
 272323  
 272324  
 272325  
 272326  
 272327  
 272328  
 272329  
 272330  
 272331  
 272332  
 272333  
 272334  
 272335  
 272336  
 272337  
 272338  
 272339  
 272340  
 272341  
 272342  
 272343  
 272344  
 272345  
 272346  
 272347  
 272348  
 272349  
 272350  
 272351  
 272352  
 272353  
 272354  
 272355  
 272356  
 272357  
 272358  
 272359  
 272360  
 272361  
 272362  
 272363  
 272364  
 272365  
 272366  
 272367  
 272368  
 272369  
 272370  
 272371  
 272372  
 272373  
 272374  
 272375  
 272376  
 272377  
 272378  
 272379  
 272380  
 272381  
 272382  
 272383  
 272384  
 272385  
 272386  
 272387  
 272388  
 272389  
 272390  
 272391  
 272392  
 272393  
 272394  
 272395  
 272396  
 272397  
 272398  
 272399  
 272400  
 272401  
 272402  
 272403  
 272404  
 272405  
 272406  
 272407  
 272408  
 272409  
 272410  
 272411  
 272412  
 272413  
 272414  
 272415  
 272416  
 272417  
 272418  
 272419  
 272420  
 272421  
 272422  
 272423  
 272424  
 272425  
 272426  
 272427  
 272428  
 272429  
 272430  
 272431  
 272432  
 272433  
 272434  
 272435  
 272436  
 272437  
 272438  
 272439  
 272440  
 272441  
 272442  
 272443  
 272444  
 272445  
 272446  
 272447  
 272448  
 272449  
 272450  
 272451  
 272452  
 272453  
 272454  
 272455  
 272456  
 272457  
 272458  
 272459  
 272460  
 272461  
 272462  
 272463  
 272464  
 272465  
 272466  
 272467  
 272468  
 272469  
 272470  
 272471  
 272472  
 272473  
 272474  
 272475  
 272476  
 272477  
 272478  
 272479  
 272480  
 272481  
 272482  
 272483  
 272484  
 272485  
 272486  
 272487  
 272488  
 272489  
 272490  
 272491  
 272492  
 272493  
 272494  
 272495  
 272496  
 272497  
 272498  
 272499  
 272500  
 272501  
 272502  
 272503  
 272504  
 272505  
 272506  
 272507  
 272508  
 272509  
 272510  
 272511  
 272512  
 272513  
 272514  
 272515  
 272516  
 272517  
 272518  
 272519  
 272520  
 272521  
 272522  
 272523  
 272524  
 272525  
 272526  
 272527

In this embodiment, a structure of the assembled lead-acid battery A' is such that there is formed a notched space 9' in lib b' at the corners of one end and the other end thereof, and a lead bushing 1 is cast in a lid portion b'1 formed at a lower level at bottom surface of the notched space 9. In this case, the height of a projection portion 1a of the lead bushing 1 from the upper surface of the lid b'1, i.e., the height h of the projection portion 1a to the upper end surface of the lead bushing 1 is set at 4 mm which is the same, as in the previous embodiment, and the upper portion 2a of a pole 2 protruding upwards from a negative strap e of a cell in a cell chamber c at one end of a battery container a' is inserted through an insertion hole 3 of the lead bushing 1. Further, a tab terminal member 10 comprising a prolong plate having the thickness of about 3 ~ 4 mm most preferably, a tab terminal member 10 comprising a prolong plate made of lead or a lead alloy, is fitly mounted on the outer peripheral surface of the columnar lead bushing 1 through a circular fitting hole 11 so made in one end thereof as to have a diameter fitly mountable on the outer surface of the lead bushing 1, and the other end of the tab terminal member 10 having a bolt-insertion hole 12 is positioned to protrude horizontally outwards from a side face of the lead-acid battery A'. It is preferable that a material for the tab terminal member 10 is the same lead alloy as that for the lead bushing 1.

Further preferably, a cylindrical mold 7' made of copper is fitly mounted on and in contact with the peripheral surface of the projection 1a of the lead bushing 1 and a semicircular peripheral surface of an outer peripheral edge of the fitted end portion 10a of the tab terminal member 10, and in addition is placed on the upper surface of the lid portion b'1 in contact with the upper surface and opposite sides of the tab terminal member 10, with a rectangular notch portion 7'b formed at the lower end of the mold 7' being across the same, so that the mold 7'b also serves to cool the lead bushing 1 at the time of the laser-welding.

For the laser welding, a laser nozzle having a condenser lens therein is disposed at a height position which is about 100 mm spaced upwards apart from the upper surface of the lead bushing 1, while the shield glass 5 is disposed below the laser nozzle 4, in the same manner as in the previous embodiment.

Figs. 4 and 5 show such a state that the mutually abutted annular portions 8 of the pole 2 and the lead bushing 1 around the outer periphery of the pole 2 have been already welded together to each other by the same laser welding as in the previous embodiment, so that a welded portion 8a has been well formed.

Further, according to the present invention, in order to weld the lead bushing 1 and the tab terminal member 10 therearound to each other, the laser welding of the both is carried out by applying a laser beam 5a from the laser nozzle 5 to mutually abutted annular portions 13 of the lead bushing 1 and the tab terminal member 10 through the glass shield 5. In this case,

00857187 052001  
F00250

as for a method of laser-welding, either a continuous welding type one or a pulsed welding type one may be adapted and the laser beam thereof is applied or irradiated, in the same manner as explained in the previous embodiment. Preferably, by the pulsed welding, a laser beam of a low output as low as 0.8 ~ 1.5 Joules/pulse is first applied to the surface of the lead terminal member 10 to expose lead inside the lead terminal member 10 to the outer surface thereof, and then, a laser beam of a high output as high as 6 ~ 8 Joules/pulse and in a range of 6 points ~ 12 points of the lap number of beads/mm is applied, thereby the laser welding of the projection 1a of the lead bushing 1 and the lead tab terminal member 10 therearound to each other is carried out, so that production of a lead-acid battery is completed.

The heat generated from the start of the laser welding to the end thereof is remarkably small, as compared with that generated by a burner, so that there is occurred no thermal deformation of the lid. It is the same as in the previous embodiment that the cooling by the mold made of copper suffices, and that the conventional water-cooling is not required.

Furthermore, when the laser welding of the tab terminal member 10 is carried out, it is optional that after either a previous soldering is applied to the portions to be welded, or a ring-shaped solder is placed thereon, and thereafter the laser welding is carried out.

Thus, according to the present invention, when the welding of the lead bushing cast in the lid of the assembled lead-acid

0057197-062004  
TOP SECRET

battery and the pole inserted through the lead bushing and further the welding of the lead bushing and the terminal member fitted on the lead bushing are carried out by the laser welding, even if the height of the lead bushing from the upper surface of the lid is remarkably lower than the case of the conventional art, a good welding can be achieved without exertion of an adverse affection onto the lid, and a stable and good lead-acid battery can be produced. Particularly, the lead-acid battery of the type having the terminal led out sideways can be produced smoothly, which is advantageous.

In this case, as mentioned above, if the laser beam of a low output of such a degree that produces no sputtering is first applied and is moved one round and thereafter a laser beam of a high output is applied and moved one round to and along the applied locus or trace of the laser beam of the low output, the laser welding of a predetermined depth can be achieved over the whole circumference without adhering sputtered leads to the shield glass. Particularly, when the pulsed type one as a laser welding method is carried out, the depth of weld can be more increased to provide a firm weld.

When the bushing 1 and the pole made of any of various kinds of lead alloys are welded to each other by applying the above-mentioned laser beam of the low output or/and the high output to the mutually abutted annular portions 8 or their vicinities and making it at least one round therealong, there is a fear that fumes generated during the welding are adhered to the shield glass 5 to intercept the passing of the laser beam

T00290-28729850

therethrough and, as a result, the welding energy is lowered, and there can not be obtained a predetermined uniform or equal depth of penetration over the whole circumference, and in some cases, there can not be obtained a lead-acid battery provided with a terminal portion welded stably and satisfactorily.

An embodiment of the present invention removing such a fear will be described in detail with reference to Figs. 6 to 10.

In Figs. 6 to 10, reference character B designates one example of a laser-welding jig according to the present invention for use in carrying out the above-mentioned laser-welding process used in the process for producing a lead-acid battery according to the present invention. A cylindrical body 70a of a cylindrical shield 70 constituting a main body of the jig B is formed into a circular one made of a metallic material having a good thermal conductivity, for instance, a metal which is high in thermal conductivity such as copper and a copper alloy, and corresponds to the mold 7 also serving as the cooling action in the previous embodiment. The cylindrical shield 70 is so constructed that an opening in the upper surface of the cylindrical body 70a is closed by a light-transmission plate 5 permeable to a laser beam, in general, by a heat-resistant glass plate 5, and the lower end portion thereof is formed into a cylindrical lower end portion 70a1 having the inner diameter suitable being fitly mounted on the outer peripheral surface of a terminal portion of a lead-acid battery. Further, the plural number, preferably, three or more of discharge openings 14, 14, ... are disposed at regular intervals

T00290-237-06204

[illegible]

50B  
A3

[illegible]

Further, at the time of using thereof a connecting tube 22 such as a pressure tube is connected at one end thereof in a band-manner to the tubular exhaust port 18 and at the other end thereof to an external vacuum pump, so that fumes generated within the jig B during the welding may be sucked and exhausted at a desired negative pressure.



Next, one example of a process for producing a lead-acid battery having a terminal welded by the above-mentioned laser-welding process according to the present invention by using the above-mentioned jig B according to the present invention will be described with reference to Figs. 9 and 10.

The lower cylindrical end portion 70a1 of the cylindrical shield 70 of the jig B according to the present invention is fitly mounted on the outer peripheral surface of a terminal portions T comprising an upper end portion 1a of a lead bushing 1 cast in a container lid b'' made of a synthetic resin in a lead-acid battery A'', and an upper end portion 2a of a positive or negative pole, e.g., of a positive pole 2 in the illustrated embodiment inserted through an insertion hole 3 of the lead bushing 2, and in other words, on an outer peripheral surface of the upper end 1a of the lead bushing 1, and therefore the inside of the cylindrical shield 70 is made airtight. On the other hand, the discharge openings 14, 14, 14 disposed in the lower portion of the cylindrical shield 70 are connected to an external common compression pump (not shown) through the connecting tubes

SUB  
 A4  
 CONT.

19, 19, 19 such as a pressure tube, and the tubular exhaust port 18 protruding from the side surface of the upper portion of the cylindrical shield 70 is connected to the external vacuum pump (not shown) through the connecting tube 21 such as a pressure tube.

SUB  
 A4

000290: 062001

A laser nozzle 4 led out, for example, from a pulsed type laser generator (not shown) is so positioned above the jig B placed on the battery lid b'' surrounding the terminals T, as described above, so that a laser beam 4b may be directed as shown by an arrow, through an incident lens within the laser nozzle 4 toward a target of the portions to be welded, i.e., toward one point of mutually abutted circular portions 8 constituting the terminal portions T composed of a projection 1a' of a lead bushing 1' and an upper portion of either a negative or a positive pole, that 2a' of the positive pole 2' in the illustrated example, inserted through the insertion bore in the lead bushing 1'. At this time, the distance between the portions 8 to be welded and the laser nozzle 4 is set to be equal to a focal distance of the incident lens within the laser nozzle 4. In the case of application of the laser beam, the laser nozzle 4 is moved round at a radius equal to the radius of the circular portions 8 to be welded, thereby applying the laser beam at least one round to the entire circumference of the portions 8 to be welded, thus welding the portions 8 together. In this case, the application conditions of the laser beam are, for example, such that a quantity of application heat is in a range of 5 ~ 10 Joules/pulse and that the application intervals are in a range

503  
753  
cont.

6 ~ 13 pps. or, as mentioned above, such a laser-welding method is carried out that the first round is made at a lower output. The speed of movement of the laser nozzle 4 is set, for example, in a range of 0.5 ~ 3.0 mm/sec.

When the welding of the portions 8 to be welded is carried out by the application of the laser beam, oxygen or air is discharged under a desired pressure into the cylindrical shield 70 through the discharge openings 14, 14, ... by the compression pump. In this case, the oxygen or air is discharged toward the open surface of the lower cylindrical end portion 70a1, i.e., toward the terminal portions T. In general, it is economically preferable that the air is used. The reflection of the laser beam can be inhibited by oxidizing the surfaces of the portions 8 to be welded by the oxygen or air during the welding, whereby the welding by the irradiation of the laser beam can be carried out at a good efficiency.

On the other hand, a decompression device such as a vacuum pump, etc. is driven to perform an evacuation at a desired negative pressure through the tubular exhaust port 18, whereby fumes generated within the cylindrical shield 70 during welding of the portions to be welded is sucked and exhausted immediately from the cylindrical shield 70 to the outside, so that the fumes are prevented from adhering to the shield glass 5 and intercepting the passing of the laser beam therethrough. Accordingly, a good laser welding of a depth of penetration uniformly welded over the whole circumference of the portions 8 without any reduction in a predetermined laser output. The shielding fluid flowed

0057187-052001

In this case, when the communication openings 15, 15, ... are made in the circumferentially tangent direction in the shroud ring 16 as mentioned above, an eddy flow is caused to occur in the flow of the exhaust gas, and the exhaust gas can be sucked to be exhausted smoothly and quickly as a flow in a given definite direction. Thus, the discharge amount of the shielding fluid to be flowed into the cylindrical shield 70 through the discharge opening 14 and the exhaust amount of the shielding fluid to be sucked and exhausted is adjusted as desired to any of various values and a desired preferable laser welding can be carried out. For this purpose, the discharge pressure and discharge flow rate of the shielding fluid by the compression pump and the exhaust pressure and exhaust rate of the exhaust fluid by the vacuum pump are adjusted to any of various values, and particularly, it is preferable to set in a range of 60 ~ 80 KPa, the discharge flow rate in a range of 15 ~ 20 liters/min, the discharge pressure in a range of 300 ~ 450 Pa and the exhaust flow rate in a range of 4 ~ 5 m<sup>3</sup>/min.

If the discharge pressure and flow rate of the shielding fluid are larger than the above-mentioned values, the fused lead

[illegible][illegible][illegible]

Furthermore, in the embodiment shown in Fig.9 above, the welding of the annular portions 8 to be welded was carried out for 100 pieces of the lead-acid battery provided with the terminal portions to be welded by applying a laser beam at a low output of 3.8 Joules/pulse while moving the first rotation (the first round) along the portions 8 to be welded to break the oxide film, and then applying a laser beam of a high output reduced stepwise at a plurality of stages, for example, of 11.5 Joules/pulse, 10.8 Joules/pulse, 10 Joules/pulse and 9.2 Joules/pulse while moving the second rotation (the second round), as shown in Fig.11. It has been found that the first round and the second round result in that the depth of weld is substantially uniformly within a range 4 ~ 6 mm over the whole circumference of the annular portions to be welded, as shown in Fig.12, and the resin of the lid b'' around the terminal portion T is not softened or molten at all, and accordingly, there can be obtained assuredly the lead-acid batteries with an air-tightness being well maintained without transuding of the electrolyte. Further, the number of the stages of the stepwise high outputs is not limited, but about 2 ~ 8 stages are preferable from the viewpoints of the quality, the producing equipment and the like.

Further, the example in which the discharge opening 14 is made in the cylindrical shield 70 and the oxygen or air is supplied therethrough has been shown as one example of the embodiment of the present invention. However, only if the fume is removed, it can be achieved only by suction through the exhaust port 18. In this case, a suitable gap is created so that

09857187-062001

compression in the cylindrical shield 70 may not be reduced. For example, it is arranged that gaps are created between the lower end portion of the cylindrical shield 70 and the surface of the lid or between the lower cylindrical end portion 70a1 and the outer peripheral surface of the terminal portions T, or that the provision of the annular packing 20 is omitted, so that the open air is flowed by the suction into the cylindrical shield 70 through a gap between the annular shield cap 19 and the glass plate 5. In this case, since the open air is flowed by the suction into the cylindrical shield 70 through these gaps, oxygen is supplied and the depth of weld can be deepened, which is preferable.

Thus, according to the present invention, since the laser welding of the terminal portions to be welded is carried out in such a manner that in such a state that the terminal portions of the lead-acid battery is surrounded by the lower cylindrical end portion of the cylindrical shield, the shield fluid is flowed thereinto through the discharge opening made in the cylindrical shield and is brought into contact with the terminal portions to be welded, and meanwhile, fumes generated during the laser welding is removed by suction through the exhaust port made in the cylindrical shield, and the reflection of the laser beam is inhibited by the shielding fluid and the laser welding can be carried out at a good efficiency, and also the intercepting of the laser beam by fumes for intercepting the laser beam can be prevented and the lowering of the sufficient laser output can be prevented and the welding efficiency is improved and also

00857187 062001

[illegible][illegible][illegible][illegible]



As for the lead bushing 1 through which the pole 2 inserted and by which it is surrounded, an outer peripheral surface of the protrusion portion 1a thereof is formed with an annular notched step 1b. A laser-welding jig B' has such a construction that an annular shield cap 20' which surrounds and holds a light-transmission glass 5', and in which the plural number of, for instance, six of circular air-intake openings 23, 23, ... each having a diameter of about 5 mm are made at equal intervals circumferentially is secured to an upper surface of a cylindrical shield 70' made of a good thermal conductivity, and an exhaust tube 21' having an inside diameter of about 30 mm is provided on an upper cylindrical wall 70a3' of the cylindrical shield 70'. In use, the laser-welding jig B' is placed so that the lower cylindrical end 70a1' thereof may be fitly mounted on the outer peripheral surface of the protrusion 1a of the lead bushing 1 and also placed on a surface of the annular notched step 1b, as shown in Fig.13. In Fig.13, reference character 15' designates a communication opening disposed in the shroud ring 16'; reference character 17' designates an annular space; and reference character 22' designates a connecting tube connected to the exhaust tube 21'.

Thus, the laser welding is carried out in such a state that the lower cylindrical end 70a1' of the laser-welding jig B' is fitly mounted on the annular notched step 1b provided on the outer peripheral surface of a terminal T, in other words, on the outer peripheral surface of the protrusion 1a of the lead bushing 1 thereof, and, in the illustrated embodiment, a laser

000250 28125800

5  
A 763

nozzle 4 is so positioned so that a laser beam 4b converged by a condenser lens 4c may be focused to hit on the outer side portion about 0.15 mm from the boundary of the annular abutted portions 8 (with a gap of 0 ~ 0.5 mm left therebetween) between the outer peripheral surface of the pole 2 and the inner peripheral surface of the lead bushing 2, and in other words, the laser beam 4b may hit on the inner peripheral edge of the lead bushing 1. And laser nozzle 4 is moved round along the inner peripheral edge of the lead bushing so that the laser beam 4b thereof may be applied thereto and, meanwhile, the evacuation by suction is conducted through the exhaust tube 21' and the connecting tube 22'. The laser welding is carried out in the above-mentioned manner that the laser beam of such a low output that generates no sputtering, was made one round and thereafter the laser beam of a high output was made one round. Thus, the laser welding between the pole 2 and the lead bushing 1 can be welded to each other satisfactorily with a uniform depth over the entire circumference. In the case, when the laser beam of the high output is made one round, it is of course that it is made one round either at a uniform or definite high output or by reducing a high output stepwise at the plural number of stages. According to the present embodiment, the open air is sucked into the cylindrical shield 70' through the air-intake openings 23, 23, ... by the above-mentioned suction evacuation action and always exhausted to the outside through the cylindrical shield 70' while carrying the fume generated in the laser welding, so that the protection glass 5 can prevent the fumes from adhering thereto

FIG. 10

and accordingly, not only the portions X to be welded can be welded together satisfactorily with a predetermined high energy and with a predetermined good depth without intercepting the laser beam, but also there is accompanied by such an effect that the lead bushing 1 heated during welding is air-cooled by the sucked exhaust current.

On the other hand, since the lower cylindrical end portion 70a1' thereof is in close contact with the notched step 1b on the outer peripheral surface of the protrusion portion 1a of the lead bushing 1, the cylindrical shield 70' made of copper takes away the heat from the lead bushing 1 and dissipates the heat to the outside to cool the protrusion portion 1a of the lead bushing 1, so that rising in the temperature of the lead bushing can be prevented together with the above-mentioned air-cooling and also melting of the welded terminal is more assuredly prevented, and after completion of the laser welding process, there is obtained a good lead-acid battery in which transuding the electrolyte through the periphery of the welded terminal portion T is prevented assuredly.

Further, the cylindrical projection 2b on the upper end surface of the pole 2 serves as an index for judging the depth of weld in accordance with such a condition of the annular portion as molten by the heat at the time of the laser welding.

Furthermore, if the projection 2a is made a solid columnar projection, the columnar projection is clamped by an alligator clip at a charging step after completion of the laser welding, and even if a spark is generated between the projection and the

S  
A  
7  
C.W.

0957187-053001

In addition, in a case where the focused point of the laser beam is so positioned as to hit on such an outer peripheral edge of the pole 2 that is inside the annular abutting portions, and the laser beam is applied along the inner peripheral edge, it is advantageous because the thermal influence exerted to the resin of the lid around the lead bushing 1 can be further reduced.

Thus, the present invention is applicable to the production of various lead-acid batteries such as a lead-acid battery for an electric automobile, a lead-acid battery for an automobile, an installed lead-acid battery and the like.